

<b>Template code</b>	WPSC-STD
<b>Template revision</b>	04
<b>Date</b>	09 May 2005
<b>Document code</b>	WPSC031
<b>Revision level</b>	04



## elixir CO2 IR - product specification sheet

Property	Unit	Range	Tolerance	Test method
Intrinsic Viscosity (IV):	dlg <sup>-1</sup>	0.82/0.84	+/-0.02	BHL0005
Melting Point:	°C	240	Minimum	BHL0015
Acetaldehyde Content:	ppm	<1.0	Maximum	BHL0003
Colour Difference: b* value:	CIEL	2.0	Maximum	BHL0001
Moisture Content:	%	<0.4	Maximum	BHL0006

- Elixir CO<sub>2</sub> IR PET resin complies with the U.S. FDA Code of Federal Regulations Title 21 part 177.1630 and EC Directive 2002/72/EC with respect to its use for food contact applications.
- Typical drying conditions:  
 Maximum acceptable moisture level: 50ppm  
 Drying air temp: 160-180°C  
 Drying air dew point: < -40°C  
 Drying residence time: 4-6hours
- Typical moulding conditions:  
 Barrel temperatures: 275-285 °C

The conditions quoted above are typical. Individual machine parameters should be determined on a machine-by-machine basis.

### Revision history - New Website Document

